West Yorkshire
Materials Testing Service
Nepshaw Lane South, Morley, Leeds, LS27 7JQ
Materials Testing Manager: D. J. Brockbank
t: 0113 393 9791
e: dale.brockbank@wyjs.org.uk
www.wyjs.org.uk/materialstesting

TEST REPORT

Client: DIRECT FABRICS

Entry No:	87555
Date received:	28/07/2017
Client's Description:	Sample of fabric Design Name: 9025 / Brace, Product Type: Inherent FR Voile
Test Required:	Flammability BS 5867-2: Type B: 2008
Pre-treatment:	Tests were made both before and after 12 washes in accordance with BS EN ISO 15028:1997 reduced wash procedure (Type A) at 40 Degrees C followed by line and press drying.
Conditioning:	A minimum of 24 hours at 65+/-5% Relative Humidity, 20+/-2°C
Date Tests Completed:	10/08/2017
Method of Test:	BS EN ISO 15025: 2002 Procedure A (surface ignition)

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

Flame application time 15 seconds using propane gas

As Received

Face of Fabric tested	**Fabric length direction**			**Fabric width direction**		
Specimen number	**1↑**	**2↓**	**3↑**	**4→**	**5←**	**6→**
Flame reached an edge (✓ or X)	**X**	**X**	**X**	**X**	**X**	**X**
Hole reached an edge (✓ or X)	**X**	**X**	**X**	**X**	**X**	**X**
Flaming debris (✓or X)	**X**	**X**	**X**	**X**	**X**	**X**

----------End of Page----------

This is hereby certified to be a correct return of the tests made of the items referred to herein

Dale Brockbank
Materials Testing Manager
10 August 2017

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- Uncertainty budgets for test methods contained within this report are available on request.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

ilac-MRA UKAS TESTING 1104

West Yorkshire Joint Services

West Yorkshire Materials Testing Service

Client: DIRECT FABRICS

Entry No: 87555

After Washing

Face of Fabric tested	Fabric length direction			Fabric width direction		
Specimen number	**1↑**	**2↓**	**3↑**	**4→**	**5←**	**6→**
Flame reached an edge (✓ or X)	**X**	**X**	**X**	**X**	**X**	**X**
Hole reached an edge (✓ or X)	**X**	**X**	**X**	**X**	**X**	**X**
Flaming debris (✓or X)	**X**	**X**	**X**	**X**	**X**	**X**

Comments

On the basis of the tests carried out this sample of fabric meets the Type B requirements of BS 5867-2: 2008 when tested as received and after washing.

----------End of Document----------