West Yorkshire
Materials Testing Service
Nepshaw Lane South, Morley, Leeds, LS27 7JQ
Materials Testing Manager: D. J. Brockbank
t: 0113 393 9791
e: dale.brockbank@wyjs.org.uk
www.wyjs.org.uk/materialstesting

TEST REPORT

Client: DIRECT FABRICS

Entry No:	82959
Date received:	10/02/2017
Client's Description:	Sample of fabric Ref: 9017, Design Name: Mirage, Product Type: Inherent FR
Test Required:	Flammability BS 5867-2: Type C: 2008 (2015)
Pre-treatment:	None
Conditioning:	A minimum of 24 hours at 65+/-5% Relative Humidity, 20+/-2°C
Date Tests Completed:	03/03/2017
Method of Test:	BS EN ISO 15025: 2002 Procedure A (surface ignition)

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

Flame application times 5, 15, 20 and 30 seconds using propane gas

Both Face and back tested	**Fabric Length direction**		**Fabric Width direction**	
Specimen number	**Face 1 ↑**	**Back 2 ↓**	**Face 3 →**	**Back 4 ←**
Flame reached an edge (✓ or X)	**X**	**X**	**X**	**X**
Hole reached an edge (✓ or X)	**X**	**X**	**X**	**X**
Flaming debris (✓or X)	**X**	**X**	**X**	**X**
Duration of flaming (s)	0	0	0	0
Duration of afterglow (s)	0	0	0	0

Comments

On the basis of the tests carried out this sample of fabric meets the Type C requirements of BS 5867-2: 2008 (2015).

----------End of Document----------

This is hereby certified to be a correct return of the tests made of the items referred to herein

Dale Brockbank
Materials Testing Manager
03 March 2017

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- Uncertainty budgets for test methods contained within this report are available on request.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

ilac-MRA UKAS TESTING 1104